

Features

- Softness、 Elastic material
- Impact resistance
- Good vibration damping performance
- High reusability
- Heat resistance
- Mildew resistance and water resistance

Application

- Seal washers
- Automobile vibration damping parts and buffer isolation
- Soft protectors
- Sports insoles
- Scenes requiring high surface ductility

Specification

Physical Properties	Test Method	Metric
Bulk Density	ASTM D1505	0.457g/cm ³
Part bed powder density	ASTM D1895	0.6g/cm ³
Part Color	Visual	White
Part Density	ISO 1183	1.2 g/cm
Water Absorption	23°C, 24h,	< 0.5% ³
Shore Hardness A	ISO 868	88
Flexural Modulus 20°C	ISO 6721-1	72 MPa
Flexural Modulus 60°C	ISO 6721-1	27 MPa
Tensile Strenght (x-direction)	DIN 53504	20 MPa
Elongation (x-direction)	DIN 53504	267%
Abrasion Resistance	ISO 4649	31 mm
Compression Stength (x-direction)	ISO 604	33 MPa
Compression Modulus(x-direction)	ISO 604	15 MPa
Vicat-softening Temperature VST A	ISO 306	90°C
Melting Temperature	ISO 11357	160°C
Powder Properties X10	Laser diff	20 μm
Powder Properties X50	Laser diff	50 μm
Powder Properties X90	Laser diff	105 μm

The TPM3D digital printing is for the relevant information of this series of products only, which, at any time, might be updated without prior notice due to technological innovations, improvements of production processes, or any necessary corrections to the printing errors and the inaccurate information.



TPM 3D Printing Technology Co.,Ltd.

Headquarters: 1F, Bldg#7,3000 Yixian Rd.,
Shanghai, China 200441

TEL: +86-21-56166181 / P.C: 200441

Emial: info@tpm3d.com / www.tpm3d.com